

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 241 231 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
18.09.2002 Bulletin 2002/38

(51) Int Cl.7: **C08L 101/00**, C08L 1/26,  
C08L 1/28, C08L 67/00,  
C08J 11/04, C09K 19/38

(21) Application number: **02005976.2**

(22) Date of filing: **15.03.2002**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **16.03.2001 JP 2001076559**

(71) Applicant: **CANON KABUSHIKI KAISHA**  
**Ohta-ku, Tokyo (JP)**

(72) Inventor: **Maehara, Hiroshi**  
**Ohta-ku, Tokyo (JP)**

(74) Representative: **Weser, Wolfgang, Dr. Dipl.-Phys.**  
**Weser & Kollegen,**  
**Patentanwälte,**  
**Radeckestrasse 43**  
**81245 München (DE)**

(54) **Resin composition, method of molding the same, and method of recycling resin composition**

(57) A resin composition which comprises a biodegradable polymer and a biodegradable liquid crystalline polymer. The resin composition is useful for producing molded resin articles having good recyclability.

**EP 1 241 231 A1**

**Description****BACKGROUND OF THE INVENTION**5 **Field of the Invention**

**[0001]** The present invention relates to a resin material of low environmental loading in consideration of global environment. The present invention also relates to a method of recycling the resin composition for material circulation to build a recycling society.

10

**Related Background Art**

**[0002]** Mankind has successively created various materials useful for daily lives and industries through the coal chemistry age and the petroleum chemistry age. In particular, the symbolic example is synthetic polymer resins including plastic materials such as polyethylene, polypropylene, and polyvinyl chloride; and rubbers such as polyisoprene, and polybutadiene. Recently, novel resin materials having excellent properties have been developed, including polyimide resins and all-aromatic liquid crystalline polymers having high heat resistance and high impact strength.

15

**[0003]** In recent years, however, in the industrial structure based on the mass production, mass consumption, and mass waste, discarded polymers cause problems. Specifically, the discarded materially stable polymer materials remain undecomposed in the soil for a long term, gradually releasing endocrine disrupters and other harmful substances to result in serious adverse effects on living things occasionally. When the polymer materials are incinerated, toxic materials such as dioxin can be generated depending on the incineration conditions to cause extreme danger. Another waste material is a large amount of waste paper discharged from offices, which also causes environmental problems.

20

**[0004]** Under such circumstances, materials and products which do not destruct the environment are wanted. Further, technical development is required which enables conservation of the environment by minimizing the consumption of global resources and recycling the materials.

25

**[0005]** On the other hand, one of the general methods for improving the properties of the polymer is introduction of a fiber structure into a polymer by blending a foreign material. Generally this method includes blending of an inorganic material such as glass fiber, and carbon fiber; blending of an organic polymer fiber such as nylon fiber, and polyester fiber; and blending of a liquid crystalline polymer having high orientability. For example, U.S. Patent 6,248,267 discloses a natural-fiber-containing nonwoven fabric. Lately the amounts of industrial waste materials and household waste materials are increasing, and the disposed materials are causing a social problem. Generally, organic polymer materials such as polyethylene and polypropylene are stable, and once discarded, they will persist in the soil for a long term. To avoid such a problem, the use of a biodegradable polymer materials is considered. However, biodegradable polymers do not have satisfactory properties in the broad range of application fields in comparison with the versatile polymer materials. The properties of a biodegradable polymer can be improved by blending of the aforementioned fiber material. However the blended filler, which is not biodegradable, renders the recycling difficult, resulting in increase of environmental loading by the persistence in the environment for a long term after the disposal.

35

40 **SUMMARY OF THE INVENTION**

**[0006]** The present invention intends to provide a resin composition useful for production of molded resin articles which can be readily recycled without remaining after disposal.

45

**[0007]** The resin composition of the present invention comprises a biodegradable polymer and a biodegradable liquid crystalline polymer.

**[0008]** The process of producing a molded resin article of the present invention comprises molding the above resin composition at a molding temperature not higher than the liquid crystal transition temperature of the liquid crystalline polymer contained in the resin composition.

**[0009]** The molded resin article of the present invention is obtained by molding the above resin composition.

50

**[0010]** The method of reusing waste paper of the present invention comprises the steps of producing at least one of a biodegradable polymer and a liquid crystalline polymer from the waste paper, and producing a resin composition of the above composition by use of the at least one polymer.

**[0011]** The method of recycling the resin composition having the above composition comprises decomposing the molded resin article composed of the resin composition to obtain a decomposition product, recovering at least one of the aforementioned biodegradable polymer and the aforementioned liquid crystalline polymer from the decomposition product, and reusing the above obtained at least one polymer for production of the resin composition.

55

**[0012]** The present invention provides a resin composition useful for producing a molded resin article which does not persist after disposal and is readily recyclable. In particular, the resin composition of the present invention can be

produced by use of a component derived from waste paper. When the molded article of this resin composition is discarded after use, the polymer component can be recycled by recovering the polymer component from the discarded molded resin article.

## 5 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS


[0013] The resin composition of the present invention contains at least a biodegradable polymer and a biodegradable liquid crystalline polymer. The resin composition of the present invention can be composed of only biodegradable components. Such a polymer does not cause the persistency problem after disposal, and can be recycled readily. The liquid crystalline polymer can give an oriented polymer molecule structure to the molded article to improve the mechanical strength of the molded article.

[0014] The biodegradable polymer employed is selected from those which are biodegradable and not liquid-crystalline, and preferably contains a sugar structure. The polymer having a sugar structure includes polymers having a sugar structure such as starch, cellulose, chitin, chitosan, pullulan, and curdlan; copolymers of D-glucose with an aliphatic dicarboxylic acid such as malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, and sebacic acid; copolymers of D-glucose with an aromatic dicarboxylic acid such as terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, and naphthalic acid; and copolymers with another compound such as polyether, polyvinyl alcohol, polymalic acid, polyhydroxyalkanoate, and polylactic acid. The biodegradable polymer selected from the above-mentioned polymers may be used singly or in combination of two or more thereof, as necessary. Of these, preferred are those containing glucose as the sugar component.


[0015] The biodegradable polymer preferably has a molecular weight (weight average) ranging from 100,000 to 5,000,000.

[0016] On the other hand, the biodegradable liquid crystalline polymer preferably has biodegradability, and has characteristics of a liquid crystal in a solution or in a molten state, and has an orientational structure.


[0017] Such a liquid crystalline polymer includes cellulose and polymers having an alkyl group on the side chain of a cellulose derivative. Examples thereof are described, for instance, in "Miyamoto, Yamagishi: Kobunshi Kako, 38, 12, (1989)", and "S.Tseng et al.: Macromolecules, 15, 1262 (1982)". Formulas (1) to (3) shows typical examples the polymer:



wherein R1, R2, and R3 independently denote hydrogen, or an aliphatic ester of 1 to 10 carbon atoms;



wherein R4, R5, and R6 independently denote hydrogen or an alkyl group of 1 to 10 carbon atoms; and



wherein R7, R8, and R9 independently denote hydrogen or a hydroxyalkyl group of 1 to 10 carbon atoms.

[0018] The cellulose derivative includes methylcellulose, ethylcellulose, carboxymethylcellulose, hydroxyethylcellulose, and hydroxypropylcellulose. The alkyl group is introduced by directly bonding an alkyl group by utilizing the three hydroxyl groups of D-glucose, a repeating unit of the cellulose molecule; by bonding an alkyl group by utilizing the hydroxyl group of hydroxyethylcellulose or hydroxypropylcellulose, by utilizing the lower alkyl groups of a cellulose derivatives such as methylcellulose, ethylcellulose, and carboxymethylcellulose, or utilizing the remaining hydroxyl groups of these compounds. The alkyl group can be bonded to the cellulose or the cellulose derivative through ester bonding, ether bonding, amide bonding, or the like. Specific examples include hydroxyalkylcellulose such as hydroxyethylcellulose and hydroxypropylcellulose, and reaction products of hydroxyalkylcellulose with an aliphatic carboxylic acid such as acetic acid, propionic acid, butyric acid, valeric acid, caproic acid, enanthic acid, caprylic acid, pelargonic acid, capric acid, undecylic acid, lauric acid, and tridecanedioic acid. Hydroxypropylcellulose is particularly preferred as the cellulose derivative for the alkyl group introduction. The liquid crystalline polymer may be employed singly or in combination of two or more thereof.

[0019] In the above Chemical Formulas (1) to (3), the degree of substitution by a substituent other than hydrogen is not lower than 20% in a molecule to develop the liquid crystal properties.

[0020] The molecular weight (weight average) of the liquid crystalline polymer ranges, for example, from about 100,000 to about 5,000,000, but is not limited thereto.

[0021] The liquid crystal transition temperature of the liquid crystalline polymer can be varied depending on the type of the alkyl group or the reaction degree in the alkyl group introduction. This temperature characteristics can be selected in consideration of the molding temperature of the blending polymer. For example, in the case where a copolymer of D-glucose and sebacic acid having a molding temperature of about 110°C is used as the biodegradable polymer, a reaction product of hydroxyethylcellulose and butyric acid is preferably used as the liquid crystalline polymer. At a degree of the substitution of 70% of hydroxyethylcellulose with butyric acid, the liquid crystal transition temperature of the reaction product is 135°C. This temperature is nearly equal to the molding temperature of the above polymer.

[0022] In blending the biodegradable polymer and the liquid crystalline polymer, the blending ratio  $(A)/((A)+(B))$ , where (A) represents the mass of the biodegradable polymer and (B) represents the mass of the liquid crystalline polymer, ranges preferably from 0.05 to 0.95.

[0023] The resin composition of the present invention is obtained by filling or blending of the liquid crystal polymer into the biodegradable polymer. The mixing of these components can be conducted by any known method.

[0024] Incidentally, use of cellulose or the like recovered from paper, especially waste paper, as the source material for the biodegradable polymer or liquid crystalline polymer can increase the recyclability of waste paper. Any known process can be employed for producing the polymer component for the resin composition from waste paper.

[0025] The simple mixture of the biodegradable polymer and the liquid crystalline polymer can be used as the resin composition. If necessary, an additive may be incorporated thereto provided that the object of the present invention is achievable. The additive includes plasticizers, pro-oxidant, age resistor, crosslinking agents, surfactants, and compatibilizing agents. The additive should be selected which causes minimum environmental loading. In use of the material in a closed system where the material is completely recycled, a usual additive may be used.

[0026] The application field of the resin composition is not limited specially. The resin composition is useful, for example, as constituent materials for ink tanks of ink-jet printers, toner containers of electrophotography apparatuses, packing materials, casings of printers and cameras, transparency sheets, and so forth.

[0027] The processing and molding conditions of the resin composition of the present invention are selected depending on the properties of the biodegradable polymer and the liquid crystalline polymer to be combined. In the case

where the biodegradable polymer is thermoplastic or thermally fusible, the molding conditions and press conditions are selected depending on the softening point, glass transition temperature, melting point, and the like thereof. The molding temperature is preferably set at a temperature not higher than the liquid crystal transition temperature of the liquid crystalline polymer, as described above. The resin composition can be molded by various molding processes including injection molding, and extrusion molding.

[0028] The molded article obtained from the resin composition of the present invention can be recycled effectively after it is discarded. For example, the molded article is decomposed by acid treatment, or high-temperature and high-pressure water treatment; the polymer components are recovered from the resulting decomposition product; and the polymer component is used as at least one source material of the resin composition of the present invention.

<Examples>

[0029] The present invention is described below in more detail by reference to examples. The unit "percent (%)" is based on mass.

(Example 1)

(Reaction of Hydroxyethylcellulose and butyric acid)

[0030] In a four-neck separable flask equipped with a refluxing device and a stirrer, was placed 39.3 g of butyric acid. Nitrogen gas was bubbled therein for one hour to replace the dissolved oxygen. Thereto 50 mL of trifluoroacetic anhydride was added gradually under a nitrogen gas flow. The temperature was elevated gradually up to 50°C by a water bath, and the activation was conducted for 30 minute. Therein 4.6 g of dried solid hydroxyethylcellulose was added gradually through an inlet: the polymer was dissolved quickly. Under this state, the reaction was continued further for 5 hours. After the reaction, the reaction mixture was poured into a large amount of water to precipitate a butyric acid ester of hydroxyethylcellulose. The obtained polymer was dried, and purified by repetition of re-dissolution in acetone and reprecipitation in water. The yield of the polymer was 6.1 g.

[0031] The obtained polymer (weight-average molecular weight: 350,845) was confirmed to be the intended substance by IR absorption spectroscopy and NMR, and found to have a liquid crystal transition temperature of 135°C by thermal analysis.

(Example 2)

(Reaction of Hydroxypropylcellulose and Iodobutane)

[0032] In a sufficiently dried four-neck separable flask equipped with a refluxing device and a stirrer, hydroxypropylcellulose (hereinafter, HPC) was dissolved in THF, and thereto a solution of n-butyllithium in hexane was added. After stirring for 30 minutes, the mixture was heated to 66°C, and thereto iodobutane was added dropwise while refluxing the THF. The mixture was allowed to react for 10 hours.

[0033] After the reaction, the reaction product was precipitated in deionized water to obtain a butyl ether compound of HPC. The obtained polymer was purified by repetition of dissolution in acetone and precipitation in deionized water.

[0034] The obtained polymer (weight-average molecular weight: 475,000) was confirmed to be the intended substance by IR absorption spectroscopy and NMR, and found to have a liquid crystal transition temperature of 125°C by thermal analysis.

(Example 3)

[0035] In a sufficiently dried four-neck separable flask equipped with a refluxing device and a stirrer, industrial alkali-cellulose was caused to react with butyl iodide in DMSO solution to produce cellulose butyl ether. After the reaction, the reaction product was precipitated in deionized water to obtain a cellulose butyl ether compound. The obtained polymer was purified by repetition of dissolution in acetone and precipitation in deionized water.

[0036] The obtained polymer (weight-average molecular weight: 255,000) was confirmed to be the intended substance by IR absorption spectroscopy and NMR, and found to have a liquid crystal transition temperature of 160°C by thermal analysis.

(Example 4)

[0037] The polymer obtained in Example 1 was dissolved in cyclohexanone with a concentration of 5%. The solution

was spin-coated on a glass substrate at a rotation speed of 3000 rpm. This substrate was observed by polarizing microscopy to confirm the molecular orientation state.

(Example 5)

[0038] An acetone solution of the polymer obtained in Example 2 was dropped onto a glass substrate and was dried. This substrate was placed on a hot plate kept at 130°C. With another glass substrate, the polymer was pressed while applying a shear stress. Then the substrate was transferred onto a cooled metal plate to cool the polymer. After cooling, the polymer was observed by polarizing microscopy to confirm molecular orientation in the direction of the force application.

(Example 6)

[0039] A DMSO solution of the polymer obtained in Example 3 was dropped onto a glass substrate and was dried. This glass substrate was placed on a hot plate kept at 170°C. With another glass substrate, the polymer was pressed while applying a shear stress. Then the substrate was transferred onto a cooled metal plate to cool the polymer. After cooling, the polymer was observed by polarizing microscopy to confirm molecular orientation in the direction of the force application.

(Example 7)

[0040] The polymer obtained in Example 1 was blended in a blending ratio of 20% with a glucose-sebacic acid copolymer which is a biodegradable resin and has a weight-average molecular weight of 50,000 to prepare a resin composition. This resin composition was molded by an injection molding machine at 140°C. The molded sample had a tensile strength improved by a factor of 1.5 in comparison with the glucose-sebacic acid copolymer before blending. The orientation of the resin was confirmed by observation of the broken-out section with electron microscopy.

(Example 8)

[0041] The polymer obtained in Example 1 was blended with a blending ratio of 25% with polyacetic acid which is a biodegradable resin and has a weight-average molecular weight of 150,000 to prepare a resin composition. This resin composition was molded by an injection molding machine at 140°C. The molded sample had a tensile strength improved by a factor of 2 in comparison with the polyacetic acid before blending.

(Example 9)

[0042] A polymer was synthesized in the same manner as in Example 3 except that a cellulose material separated from waste paper was used in place of the industrial cellulose as the source material. The obtained polymer was similar to the polymer obtained in Example 3 in appearance and properties.

(Example 10)

[0043] A transparency sheet was prepared by blending the butyl ester of hydroxyethylcellulose (HEC) obtained in Example 1 with polylactic acid, and press-molding the resulting blend. This sheet has excellent transparency because of no light absorption in the visible light region. This sheet was compatible with ink and had excellent printability since this sheet is based on cellulose source material. Furthermore, owing to a single layer structure of the sheet formed from the resin composition of the present invention, this sheet did not cause curling or other deformation which may be caused in multilayered sheets due to difference in thermal expansion coefficients at temperature rise.

(Example 11)

[0044] The transparency sheet molded in Example 10 was shredded into chips by a shredder. The sheet chips were decomposed by action of fuming hydrochloric acid (at a temperature of 25°C), or high-temperature and high-pressure water (at a pressure of 35 MPa and a temperature of 400°C). The glucose chemically separated from the decomposition product was used as a source material for synthesis of glucose-sebacic acid copolymer.

(Example 12)


[0045] The transparent sheet molded in Example 10 was melted and pressed again to mold a transparency sheet. This sheet was found to be usable as a transparency sheet without causing problem in light transmissivity and other properties.

(Example 13)

[0046] The transparency sheet molded in Example 10 was melted, and pelletized, and was molded by an injection machine into a casing of an ink-jet printer. The casing was formed without problem in molding.


# Claims

1. A resin composition, comprising a biodegradable polymer and a biodegradable liquid crystalline polymer.
2. The resin composition according to claim 1, wherein the biodegradable polymer comprises a sugar structure.
3. The resin composition according to claim 2, wherein the sugar structure contains glucose.
4. The resin composition according to claim 3, wherein the structure containing glucose is a structure in which the glucose and a dicarboxylic acid are bonded.
5. The resin composition according to claim 1, wherein the liquid crystalline polymer has a structure represented by Formula (1):




wherein R1, R2, and R3 independently denote hydrogen, or an aliphatic ester of 1 to 10 carbon atoms.

6. The resin composition according to claim 1, wherein the liquid crystalline polymer has a structure represented by Formula (2):



wherein R4, R5, and R6 independently denote hydrogen or an alkyl group of 1 to 10 carbon atoms.

7. The resin composition according to claim 1, wherein the liquid crystalline polymer has a structure represented by Formula (3):



wherein R7, R8, and R9 independently denote hydrogen or a hydroxyalkyl group of 1 to 10 carbon atoms.

8. The resin composition according to claim 7, wherein the liquid crystalline polymer is hydroxypropylcellulose.
9. The resin composition according to claim 1, wherein a blending ratio of (A)/((A)+(B)) ranges from 0.05 to 0.95, where (A) represents the mass of the biodegradable polymer and (B) represents the mass of the liquid crystalline polymer.
10. The resin composition according to claim 1, wherein the liquid crystalline polymer has an orientation structure.
11. The resin composition according to claim 1, wherein at least one of the biodegradable polymer and the liquid crystalline polymer is derived from waste paper.
12. A process for producing a molded resin article, comprising the steps of:
- preparing a resin composition containing a biodegradable polymer and a biodegradable liquid crystalline polymer, and  
molding the resin composition at a temperature not higher than the liquid crystal transition temperature of the liquid crystalline polymer.
13. A molded resin article, formed by molding a resin composition containing a biodegradable polymer and a biodegradable liquid crystalline polymer.
14. A method of recycling waste paper, comprising the steps of:
- producing at least one of a biodegradable polymer and a biodegradable liquid crystalline polymer, from waste paper, and  
producing a resin composition by using the at least one polymer produced.
15. A method for recycling a resin composition containing a biodegradable polymer and a biodegradable liquid crystalline polymer, comprising the steps of:
- decomposing a molded article formed from the resin composition to obtain a decomposition product,  
recovering at least one of the biodegradable polymer and the biodegradable liquid crystalline polymer, and  
reusing the recovered at least one polymer for producing the resin composition.
16. The method according to claim 15, wherein the resin composition of the molded article is decomposed by treatment with an acid.



17. The method according to claim 15, wherein the decomposition step of the molded article is carried out by a treatment with high-temperature and high-pressure water.

5

10

15

20

25

30

35

40

45

50

55



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 02 00 5976

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IntCl.7)
X	<p>DATABASE WPI Week 198330 Derwent Publications Ltd., London, GB; AN 1983-720374 XP002203935 "Cellulose acetate molding compsn. of good shape stability - contains cellulose acetate and cellulose ester of lower polymerisation degree than the acetate." &amp; JP 58 103538 A (DAICEL CHEM IND LTD), 20 June 1983 (1983-06-20) * abstract *</p>	1-3,5,9, 10,12,13	<p>C08L101/00 C08L1/26 C08L1/28 C08L67/00 C08J11/04 C09K19/38</p>
A	<p>US 5 244 945 A (ELION) 14 September 1993 (1993-09-14) * abstract * * column 1, line 10 - line 35 *</p>	1,5,11, 14	
A	<p>EP 0 535 650 A (MAZDA MOTOR CORPORATION) 7 April 1993 (1993-04-07) * abstract; claims *</p>	1,12	TECHNICAL FIELDS SEARCHED (IntCl.7)
A	<p>EP 0 637 614 A (MAZDA MOTOR CORPORATION) 8 February 1995 (1995-02-08) * abstract; claims *</p>	1,12	C08L
A	<p>DATABASE WPI Week 198541 Derwent Publications Ltd., London, GB; AN 1985-252567 XP002203936 "Water-resistant cellulose material moulding prodn. - by esterifying mixt. of epoxy cpd. and carboxyl contg. esterified cellulose material" &amp; JP 60 166301 A (OKURA IND CO LTD), 29 August 1985 (1985-08-29) * abstract *</p>	11	
-/-			
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>28 June 2002</b>	Examiner <b>Mazet, J-F</b>
CATEGORY OF CITED DOCUMENTS		<p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons            &amp; : member of the same patent family, corresponding document</p>	
<p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p>			

EPO FORM 1503 (3-92) (P04C01)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 00 5976

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
P, A	<p>DATABASE WPI Week 200212 Derwent Publications Ltd., London, GB; AN 2002-085382 XP002203937 "High molecular compound for molded articles such as containers, comprises ester of glucose and aliphatic dicarboxylic acid in principal chain, with one or more of the hydroxyl groups being acetylated" &amp; JP 2001 226406 A (CANON KK), 21 August 2001 (2001-08-21) * abstract *</p>	1-4, 11, 14	<p>TECHNICAL FIELDS SEARCHED (Int.Cl.7)</p>
A	<p>DATABASE WPI Week 199723 Derwent Publications Ltd., London, GB; AN 1997-252618 XP002203938 "Production of speaker frames - which comprise fibrils of thermotropic liquid crystal ester resin dispersed in thermoplastic resin matrix" &amp; JP 09 084183 A (ONKYO KK), 28 March 1997 (1997-03-28) * abstract *</p>	1, 12, 13, 15	
A	<p>US 5 021 475 A (ISAYEV) 4 June 1991 (1991-06-04) * column 1, line 27 - column 2, line 3 * * column 3, line 8 - line 40 * --- -/--</p>	1, 6, 9, 10, 12, 13	
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>28 June 2002</b>	Examiner <b>Mazet, J-F</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p>		<p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons --- &amp;: member of the same patent family, corresponding document</p>	

EPO FORM 1503 (3.92) (P04C01)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 00 5976

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InCL7)
A	<p>DATABASE WPI Week 198814 Derwent Publications Ltd., London, GB; AN 1988-095555 XP002203939 "Rubber composn. with good friction and abrasion resistance - comprises rubber compounded with liq. crystal polymer powder, e.g. poly-gamma-ethyl-L-glutarate" &amp; JP 63 046242 A (NIPPON OIL SEAL IND CO LTD), 27 February 1988 (1988-02-27) * abstract *</p>	1,5, 7-10,12, 13	
A	<p>DATABASE CHEMABS 'Online! Chemical Abstracts Service, Columbus, Ohio, US; "Study on the rheological behavior of thermotropic liquid crystalline cellulose derivatives and their thermoplastics composites." retrieved from STN Database accession no. 126:279160 XP002203933 * abstract * &amp; LI, BAIGIAN ET AL.: GAOFENZI CAILIAO KEXUE YU GONGCHENG, vol. 13, no. 2, 1997, pages 109-112, --- -/-</p>		<p>TECHNICAL FIELDS SEARCHED (InCL7)</p>
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>28 June 2002</b>	Examiner <b>Mazet, J-F</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons --- &amp;: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 00 5976

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	<p>DATABASE CHEMABS 'Online! Chemical Abstracts Service, Columbus, Ohio, US; "Cellulose polymers as functional materials. Liquid crystal formation and biodegradability." retrieved from STN Database accession no. 125:89367 XP002203934 * abstract * &amp; NISHIO YOSHIYUKI ET AL.: SHINSOZAI, vol. 7, no. 5, 1996, pages 8-12,</p>		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>28 June 2002</b>	Examiner <b>Mazet, J-F</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 00 5976

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-06-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 58103538	A	20-06-1983	NONE	
US 5244945	A	14-09-1993	AU 4668693 A WO 9402539 A1	14-02-1994 03-02-1994
EP 535650	A	07-04-1993	JP 3224136 B2 JP 5086257 A JP 3217091 B2 JP 5086288 A JP 3115655 B2 JP 5086268 A JP 3162124 B2 JP 5086234 A JP 3119508 B2 JP 5112709 A JP 3241404 B2 JP 5084801 A JP 3124587 B2 JP 5086273 A JP 3159741 B2 JP 5086282 A JP 3217092 B2 JP 5086286 A JP 3224137 B2 JP 5086258 A EP 0535650 A2 KR 9606785 B1 DE 69230201 D1 DE 69230201 T2 EP 0524655 A2 KR 9605588 B1 US 5632945 A	29-10-2001 06-04-1993 09-10-2001 06-04-1993 11-12-2000 06-04-1993 25-04-2001 06-04-1993 25-12-2000 07-05-1993 25-12-2001 06-04-1993 15-01-2001 06-04-1993 23-04-2001 06-04-1993 09-10-2001 06-04-1993 29-10-2001 06-04-1993 07-04-1993 23-05-1996 02-12-1999 13-07-2000 27-01-1993 26-04-1996 27-05-1997
EP 637614	A	08-02-1995	EP 0637614 A2 JP 7117049 A	08-02-1995 09-05-1995
JP 60166301	A	29-08-1985	JP 1446915 C JP 62058603 B	30-06-1988 07-12-1987
JP 2001226406	A	21-08-2001	NONE	
JP 9084183	A	28-03-1997	NONE	
US 5021475	A	04-06-1991	CA 2010103 A1	15-08-1991
JP 63046242	A	27-02-1988	NONE	

EPO FORM P0450

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82